

AN 97:145765 HCA
 TI Polypropylene molding compositions
 PA Mitsubishi Petrochemical Co., Ltd., Japan
 SO Jpn. Kokai Tokkyo Koho, 9 pp.
 CODEN: JKXXAF
 DT Patent
 LA Japanese
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP--57076041	A2	19820512	1980JP-0151861	19801029
PRAI	1980JP-0151861		19801029		

AB polypropylene (I) [9003-07-0]-based moldings having good molding and coating processability contain unsatd. acid-grafted I, 0.5-30% petroleum resins, and 10-60% of inorg. fillers having aspect ratio ≥ 3 with or without glass fibers. Thus, a compn. of maleic anhydride (II)-grafted I (0.6 II units) 5, I 40, Hiresin 2P (petroleum resin) 10, and mica (aspect ratio 13) 45 parts was extruded, pelletized, and injection molded to give test pieces having adhesion of an acrylic coating (cross-cut test) 100/100, flexural strength 20,500 kg/cm², and warp (260-77-diam. .times. 2-mm disk) 1.2% (based on diam.), compared with 10/100, 9000, and 1.8, resp., for a similar compn. contg. CaCO₃ instead of mica.

IT Coating materials

(acrylic polymers, adhesion of, to polypropylene moldings contg. unsatd. acid-grafted polypropylene-petroleum resin-mica compns.)

IT Petroleum resins

RL: USES (Uses)

(polypropylene molding compns. contg. unsatd. acid-modified polypropylene and mica and)

IT Mica-group minerals, uses and miscellaneous

RL: USES (Uses)

(polypropylene molding compns. contg. unsatd. acid-modified polypropylene and petroleum resin and)

IT Plastics, molded

RL: USES (Uses)

(polypropylene-unsatd. acid-grafted polypropylene-petroleum resin-mica compns.)

IT 9010-79-1

RL: USES (Uses)

(block, molding compns., contg. unsatd. acid-grafted polypropylene-petroleum resin-mica compns.)

IT 25214-24-8 25722-45-6

RL: USES (Uses)

(graft, polypropylene molding compns. contg. petroleum resin and mica and)

IT 9003-07-0

RL: USES (Uses)

(molding compns., contg. unsatd. acid-grafted polypropylene-petroleum resin-mica compns.)